



23 June 2022

VALTEC SOLUTIONS CONSTRUCTION INC
7690, rue de Lamartine
Anjou, Quebec H1J 2A8
Canada

Project Name: 22-005233 - TECNICA
Project Address: 9151 BLV. SAINT-LAURENT MONTREAL, Quebec H2N 1N2 Canada
Sample Test Name: CIOT INC.

Ref.: ADHESION Test Report for TECNICA - CIOT INC.

Dear Administration Valtec,

The Dow construction laboratory has completed the adhesion testing in support of your above referenced project. The adhesion tests are performed in accordance to the adapted ASTM C794. A summary of this laboratory testing / evaluation and application recommendations is given below.

1. Sample Nr 242403	Substrate Details	
Substrate Type	Other Substrate	
Substrate Mnf Name / Supplier Name	CIOT	
Substrate Description	Fiberglass Mesh Back Of A NEOLITHE Tile	
Surface to Test	Back	
Cleaner	70/30 Isopropanol / Water	
Sealant	Primer	Application Recommendation
DOWSIL™ 795 Silicone Building Sealant	DOWSIL™ 1200 OS Primer	Approved for Structural and Weatherseal Applications
DOWSIL™ 795 Silicone Building Sealant	No Primer	Approved for Structural and Weatherseal Applications



23 June 2022

2. Sample Nr 242404		Substrate Details	
Substrate Type		Other Substrate	
Substrate Mnf Name / Supplier Name		CIOT INC.	
Substrate Description		Neolith Tile	
Surface to Test		Edge	
Cleaner		70/30 Isopropanol / Water	
Sealant		Primer	Application Recommendation
DOWSIL™ 795 Silicone Building Sealant		DOWSIL™ 1200 OS Primer	Approved for Weatherseal Applications
DOWSIL™ 795 Silicone Building Sealant		No Primer	Testing indicates that the sealant failed to achieve adequate adhesion to the substrate, Do NOT Use

Surfaces that are cleaned and primed today must be sealed today; otherwise recleaning and repriming are required before application.

Application recommendations are based on Dow laboratory testing, evaluation and technical specifications.

It is recommended that regular jobsite adhesion testing be performed throughout the project to confirm that good adhesion is obtained consistently on actual job site substrates. Information and literature on field adhesion testing and Dow application procedures may be obtained by contacting your Dow distributor or customer service representative or in the Dow Construction Technical Manuals located under <http://www.dow.com/construction>.

DOW HIGH PERFORMANCE BUILDING*Imagine the Possibilities*consumer.dow.com/Construction**AMERICAS**

Sealant Test Lab, DC-4, Lab 3A4
2200 W.Salzburg Road
Auburn, MI 48611
USA
Phone : + 1-800-346-9882
americas.cool@dow.com

ASIA

Shanghai Dow Center
936 Zhangheng Road
Pudong District, Shanghai
201203 P. R. China
Phone: +86 21 38511100
asia.cool@dow.com

EMEAI

Parc Industriel – Zone C
B-7180 Seneffe
Belgium
Phone: + 32 (0) 64 511 156
Fax: +32 (0) 270 62 319
emeai.cool@dow.com



The Dow Chemical Company

23 June 2022

Sincerely,

Scott Waechter
BUSINESS DEVELOPMENT SPECIALIST

Customer - CIOT INC.
Address: 9151 BLV. ST-LAURENT MONTREAL, Quebec H2N 1N2 Canada

CC: Valtec

Page 3 of 3

DOW HIGH PERFORMANCE BUILDING

Imagine the Possibilities
consumer.dow.com/Construction

DOWSIL™

silicones by 

AMERICAS

Sealant Test Lab, DC-4, Lab 3A4
2200 W.Salzburg Road
Auburn, MI 48611
USA
Phone : + 1-800-346-9882
americas.cool@dow.com

ASIA

Shanghai Dow Center
936 Zhangheng Road
Pudong District, Shanghai
201203 P. R. China
Phone: +86 21 38511100
asia.cool@dow.com

EMEA

Parc Industriel – Zone C
B-7180 Seneffe
Belgium
Phone: + 32 (0) 64 511 156
Fax: +32 (0) 270 62 319
emeai.cool@dow.com

General Business